

Datasheet: EN 1.4301/304 – Austenite Welded Tubes - Stainless Steel Alumeco ApS 05-12-2024					Internal alloy name: 1.4301 Alloy type: Austenite Chemical Symbol: X5CrNi18-10 EN: EN 1.4301 AISI: 304 UNS: S30400 SS: 2333 JIS: SUS304 GB: S30408																								
Main usage: - Household appliances and consumer goods - Kitchen equipment - Indoor and outdoor cladding, handrails, and window frames - Food and beverage industry equipment - Storage tanks - Flanges and valves			Important norms and literature: General Standards EN 10088-1: List of stainless Steel Geometric Tolerance: EN 1127 D3/T3: Stainless steel tubes- Dimensions, tolerances and conventional masses per unit length Product standards: EN 10217-7: Welded steel tubes for pressure purposes- Technical delivery conditions-Part 7: Stainless steel tubes ASTM A554-98E1: Standard specification for welded stainless steel mechanical tubing																										
Main properties: - Excellent weldability - Good stability against corrosion - Good formability, both cold and hot																													
Chemical composition in %: EN 10217-7 <table><tr><td>C</td><td>Si</td><td>Mn</td><td>P</td><td>S</td><td>Cr</td><td>Mo</td><td>Ni</td><td>Remarks</td><td>Rest</td></tr><tr><td>≤ 0,07</td><td>≤ 1,00</td><td>≤ 2,00</td><td>≤ 0,045</td><td>≤ 0,030*</td><td>17,5 - 19,5</td><td>-</td><td>8,0 - 10,5</td><td>N ≤ 0,10</td><td>Fe</td></tr></table> * For machinability, a controlled sulfur content of 0,015%-0,030% is recommended & permitted. For weldability a controlled sulfur content of 0,008%- 0,030% is recommended & permitted. For polishability, a controlled sulfur content of 0,015% is recommended.										C	Si	Mn	P	S	Cr	Mo	Ni	Remarks	Rest	≤ 0,07	≤ 1,00	≤ 2,00	≤ 0,045	≤ 0,030*	17,5 - 19,5	-	8,0 - 10,5	N ≤ 0,10	Fe
C	Si	Mn	P	S	Cr	Mo	Ni	Remarks	Rest																				
≤ 0,07	≤ 1,00	≤ 2,00	≤ 0,045	≤ 0,030*	17,5 - 19,5	-	8,0 - 10,5	N ≤ 0,10	Fe																				
Mechanical properties: EN 10217-7 <table><tr><td>Outer diameter (mm)</td><td>Wall thickness (mm)</td><td>Rm MPa</td><td>Rp_{0,2} MPa</td><td>Rp_{1,0} MPa</td><td>Elongation (Longitudinal) A%</td><td>Impact energy (Longitudinal) KV₂</td><td>Hardness* HB</td></tr><tr><td>21,3 - 600</td><td>1,3 - 3</td><td>500 - 700</td><td>Min. 195</td><td>Min. 230</td><td>40</td><td>100</td><td>-</td></tr></table> * Information values only;										Outer diameter (mm)	Wall thickness (mm)	Rm MPa	Rp _{0,2} MPa	Rp _{1,0} MPa	Elongation (Longitudinal) A%	Impact energy (Longitudinal) KV ₂	Hardness* HB	21,3 - 600	1,3 - 3	500 - 700	Min. 195	Min. 230	40	100	-				
Outer diameter (mm)	Wall thickness (mm)	Rm MPa	Rp _{0,2} MPa	Rp _{1,0} MPa	Elongation (Longitudinal) A%	Impact energy (Longitudinal) KV ₂	Hardness* HB																						
21,3 - 600	1,3 - 3	500 - 700	Min. 195	Min. 230	40	100	-																						
Physical properties: <table><tr><td>Density g/cm³</td><td>Electrical resistivity Ω mm² / m</td><td>Thermal conductivity W/m K</td><td>Thermal expansion (µm m⁻¹ K⁻¹)</td><td>Specific heat (J kg⁻¹ K⁻¹)</td><td>E - modulus (N / mm²)</td><td>Magnetizable</td><td>PREN (Min.)</td></tr><tr><td>7,9</td><td>0,73</td><td>15</td><td>16,0</td><td>500</td><td>200.000</td><td>No</td><td>17,5</td></tr></table>										Density g/cm³	Electrical resistivity Ω mm² / m	Thermal conductivity W/m K	Thermal expansion (µm m ⁻¹ K ⁻¹)	Specific heat (J kg ⁻¹ K ⁻¹)	E - modulus (N / mm²)	Magnetizable	PREN (Min.)	7,9	0,73	15	16,0	500	200.000	No	17,5				
Density g/cm³	Electrical resistivity Ω mm² / m	Thermal conductivity W/m K	Thermal expansion (µm m ⁻¹ K ⁻¹)	Specific heat (J kg ⁻¹ K ⁻¹)	E - modulus (N / mm²)	Magnetizable	PREN (Min.)																						
7,9	0,73	15	16,0	500	200.000	No	17,5																						
Typical Alumeco products with this alloy Outer Dia: 21.3 (3.5'')-606 mm (21.3'') ; Wall Thickness: 1.6-3 mm																													

Tolerances for welded steel tubes for EN 1.4301:

Tolerances on outside diameter	
Tolerance class	Tolerance on outside diameter
D ₁	± 1,5% with min. ± 0,75 mm
D ₂	± 1% with min. ± 0,5 mm
D ₃	± 0,75% with min. ± 0,3 mm
D ₄	± 0,5% with min. ± 0,1 mm

* Values are referred from Table 1 of EN 1127:1992

Tolerances on thickness	
Tolerance class	Tolerance on thickness
T ₁	± 15% with min. ± 0,6 mm
T ₂	± 12,5% with min. ± 0,4 mm
T ₃	± 10% with min. ± 0,2 mm
T ₄	± 7,5% with min. ± 0,15 mm
T ₅	± 5% with min. ± 0,1 mm

* Values are referred from Table 2 of EN 1127:1992

Tolerances on exact lengths	
Length L (mm)	Tolerance on exact length (mm)
$L \leq 6000$	+ 5 0
$6000 < L \leq 12000$	+10 0
$L > 12000$	+ by agreement 0

* Values are referred from Table 12 of EN 10217-7:2014