

Datasheet: EN 1.4301/304 – Austenite Round Bars - Stainless Steel Alumeco ApS 06-03-2025				Internal alloy name: 1.4301 Alloy type: Austenite Chemical Symbol: X5CrNi18-10 EN: EN 1.4301 AISI: 304 UNS: S30400 SS: 2333 JIS: SUS304 GB: S30408																									
Main usage: - Household appliances and consumer goods - Kitchen equipment - Indoor and outdoor cladding, handrails, and window frames - Food and beverage industry equipment - Storage tanks - Flanges and valves			Important norms and literature: General Standards: EN 10088-1: List of stainless Steel Product standards: EN 10088-3: Technical delivery conditions for semi-finished products, bars, rods, wire, sections and bright products of corrosion resisting steels for general purposes Geometric Tolerance: EN 10060: Hot rolled round steel bars for general purposes – Dimensions and tolerances on shape and dimensions. EN 10278: Dimensions & tolerances of bright steel products																										
Main properties: - Excellent weldability - Good stability against corrosion - Good formability, both cold and hot																													
Chemical composition in %: EN 10088-1 <table><tr><td>C</td><td>Si</td><td>Mn</td><td>P</td><td>S</td><td>Cr</td><td>Mo</td><td>Ni</td><td>Remarks</td><td>Rest</td></tr><tr><td>≤ 0,07</td><td>≤ 1,00</td><td>≤ 2,00</td><td>≤ 0,045</td><td>≤ 0,030*</td><td>17,5-19,5</td><td>-</td><td>8,0-10,5</td><td>N ≤ 0,10</td><td>Fe</td></tr></table> * For machinability, a controlled sulfur content of 0,015%-0,030% is recommended & permitted. For weldability a controlled sulfur content of 0,008%- 0,030% is recommended & permitted. For polishability, a controlled sulfur content of 0,015% is recommended.										C	Si	Mn	P	S	Cr	Mo	Ni	Remarks	Rest	≤ 0,07	≤ 1,00	≤ 2,00	≤ 0,045	≤ 0,030*	17,5-19,5	-	8,0-10,5	N ≤ 0,10	Fe
C	Si	Mn	P	S	Cr	Mo	Ni	Remarks	Rest																				
≤ 0,07	≤ 1,00	≤ 2,00	≤ 0,045	≤ 0,030*	17,5-19,5	-	8,0-10,5	N ≤ 0,10	Fe																				
Mechanical properties: EN 10088-3 <table><tr><td>Dim. range (mm)</td><td>Temper</td><td>Rm MPa</td><td>Rp0,2 MPa</td><td>Rp1,0 MPa</td><td>Elongation (Longitudinal) A%</td><td>Impact energy (Longitudinal) KV₂</td><td>Hardness* HB</td></tr><tr><td>3-12</td><td>Hot rolled</td><td>520 - 720</td><td>Min. 210</td><td>Min. 250</td><td>45</td><td>100</td><td>Max. 215</td></tr></table> * Information values only;										Dim. range (mm)	Temper	Rm MPa	Rp0,2 MPa	Rp1,0 MPa	Elongation (Longitudinal) A%	Impact energy (Longitudinal) KV ₂	Hardness* HB	3-12	Hot rolled	520 - 720	Min. 210	Min. 250	45	100	Max. 215				
Dim. range (mm)	Temper	Rm MPa	Rp0,2 MPa	Rp1,0 MPa	Elongation (Longitudinal) A%	Impact energy (Longitudinal) KV ₂	Hardness* HB																						
3-12	Hot rolled	520 - 720	Min. 210	Min. 250	45	100	Max. 215																						
Physical properties: <table><tr><td>Density g/cm³</td><td>Electrical resistivity Ω mm² / m</td><td>Thermal conductivity W/m K</td><td>Thermal expansion (µm m⁻¹ K⁻¹)</td><td>Specific heat (J kg⁻¹ K⁻¹)</td><td>E - modulus (N / mm²)</td><td>Magnetizable</td><td>PREN (Min.)</td></tr><tr><td>7,9</td><td>0,73</td><td>15</td><td>16,0</td><td>500</td><td>200.000</td><td>No</td><td>17,5</td></tr></table>										Density g/cm ³	Electrical resistivity Ω mm ² / m	Thermal conductivity W/m K	Thermal expansion (µm m ⁻¹ K ⁻¹)	Specific heat (J kg ⁻¹ K ⁻¹)	E - modulus (N / mm ²)	Magnetizable	PREN (Min.)	7,9	0,73	15	16,0	500	200.000	No	17,5				
Density g/cm ³	Electrical resistivity Ω mm ² / m	Thermal conductivity W/m K	Thermal expansion (µm m ⁻¹ K ⁻¹)	Specific heat (J kg ⁻¹ K ⁻¹)	E - modulus (N / mm ²)	Magnetizable	PREN (Min.)																						
7,9	0,73	15	16,0	500	200.000	No	17,5																						
Typical Alumeco products with this alloy Round bars - Dim: 6-300 mm x Length: 3000 mm																													

Tolerances for rounded bars for EN 1.4301:

Tolerances classes				
Diameter d (mm)	Tolerance classes to ISO 286-2			
	H9	H10	H11	H12
$6 < d \leq 10$	+0 -0,036	+0 -0,058	+0 -0,090	+0 -0,150
$10 < d \leq 18$	+0 -0,043	+0 -0,070	+0 -0,110	+0 -0,180
$18 < d \leq 30$	+0 -0,052	+0 -0,084	+0 -0,130	+0 -0,210
$30 < d \leq 50$	+0 -0,062	+0 -0,100	+0 -0,160	+0 -0,250
$50 < d \leq 80$	+0 -0,074	+0 -0,120	+0 -0,190	+0 -0,300
$80 < d \leq 120$	+0 -0,087	+0 -0,140	+0 -0,220	+0 -0,350
$120 < d \leq 180$	+0 -0,100	+0 -0,160	+0 -0,250	+0 -0,400
$180 < d \leq 200$	+0 -0,115	+0 -0,185	+0 -0,290	+0 -0,460

* Values are referred from Table 2 of EN 10278:1999

Tolerance deviation k (for shafts)	
Specified length d (mm)	ISO K Tolerances (mm) k11
$25 < d \leq 30$	+0,130 0
$30 < d \leq 50$	+0,160 0
$50 < d \leq 80$	+0,190 0
$80 < d \leq 120$	+0,220 0
$120 < d \leq 180$	+0,250 0
$180 < d \leq 250$	+0,290 0
$250 < d \leq 300$	+0,320 0

Deviation from straightness			
Product form	Steel group	Nominal dimension	Deviation max. (mm)
Rounds	< 0,25% C		1,0
	≥ 0,25% C, alloy steels, quenched and tempered steels		1,5
	Stainless steels, ball and roller bearing steels, tool steels		1,0

* Values are referred from Table 4 of EN 10278:1999

Types of length and length tolerances			
Type of length	Length (mm)	Length tolerances (mm)	To be stated on order
Manufacturing length	$3000 < L \leq 9000$	±500	Length
Stock length	3000 or 6000	0 +200	1,5
Cut to length	< 9000	±5	1,0

* Values are referred from Table 5 of EN 10278:1999